

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

| | | |
|--|-----------|--|
| (51) International Patent Classification ⁶ : H01B 3/44, 3/20 | A1 | (11) International Publication Number: WO 99/13477 (43) International Publication Date: 18 March 1999 (18.03.99) |
| (21) International Application Number: PCT/DK98/00382 (22) International Filing Date: 9 September 1998 (09.09.98) (30) Priority Data: 1027/97 9 September 1997 (09.09.97) DK (71) Applicant (for all designated States except US): NKT RESEARCH CENTER A/S [DK/DK]; Priorparken 878, DK-2605 Brøndby (DK). (72) Inventors; and (75) Inventors/Applicants (for US only): STRØBECH, Esben, Rune [DK/DK]; Selmersvej 11, DK-2970 Høsholm (DK). WINTER-JENSEN, Bjørn [DK/DK]; Homemannsgade 17, DK-2100 Copenhagen Ø (DK). GLEJBØL, Kristian [DK/DK]; Fiskerhusene 8, DK-2620 Albertslund (DK). (74) Agent: HOFMAN-BANG & BOUTARD, LEHMANN & REE A/S; Hans Bekkevolds Allé 7, DK-2900 Hellerup (DK). | | (81) Designated States: AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>With amended claims.</i> <i>In English translation (filed in Danish).</i> |
| (54) Title: AN ELECTRICALLY INSULATING MATERIAL, METHOD FOR THE PREPARATION THEREOF, AND INSULATED OBJECTS COMPRISING SAID MATERIAL | | |
| (57) Abstract An electrically insulating material comprising a continuous phase of a thermoplastic polymer and an additional phase incorporated herein of a liquid or easily meltable dielectric in the form of a wholly or partly interpenetrating network, and where the weight ratio of polymer to dielectric is between 95:5 and 25:75. | | |

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

| | | | | | | | |
|----|--------------------------|----|--|----|--|----|--------------------------|
| AL | Albania | ES | Spain | LS | Lesotho | SI | Slovenia |
| AM | Armenia | FI | Finland | LT | Lithuania | SK | Slovakia |
| AT | Austria | FR | France | LU | Luxembourg | SN | Senegal |
| AU | Australia | GA | Gabon | LV | Latvia | SZ | Swaziland |
| AZ | Azerbaijan | GB | United Kingdom | MC | Monaco | TD | Chad |
| BA | Bosnia and Herzegovina | GE | Georgia | MD | Republic of Moldova | TG | Togo |
| BB | Barbados | GH | Ghana | MG | Madagascar | TJ | Tajikistan |
| BE | Belgium | GN | Guinea | MK | The former Yugoslav Republic of Macedonia | TM | Turkmenistan |
| BF | Burkina Faso | GR | Greece | ML | Mali | TR | Turkey |
| BG | Bulgaria | HU | Hungary | MN | Mongolia | TT | Trinidad and Tobago |
| BJ | Benin | IE | Ireland | MR | Mauritania | UA | Ukraine |
| BR | Brazil | IL | Israel | MW | Malawi | UG | Uganda |
| BY | Belarus | IS | Iceland | MX | Mexico | US | United States of America |
| CA | Canada | IT | Italy | NE | Niger | UZ | Uzbekistan |
| CF | Central African Republic | JP | Japan | NL | Netherlands | VN | Viet Nam |
| CG | Congo | KE | Kenya | NO | Norway | YU | Yugoslavia |
| CH | Switzerland | KG | Kyrgyzstan | NZ | New Zealand | ZW | Zimbabwe |
| CI | Côte d'Ivoire | KP | Democratic People's Republic of Korea | PL | Poland | | |
| CM | Cameroon | KR | Republic of Korea | PT | Portugal | | |
| CN | China | KZ | Kazakhstan | RO | Romania | | |
| CU | Cuba | LC | Saint Lucia | RU | Russian Federation | | |
| CZ | Czech Republic | LI | Liechtenstein | SD | Sudan | | |
| DE | Germany | LK | Sri Lanka | SE | Sweden | | |
| DK | Denmark | LR | Liberia | SG | Singapore | | |
| EE | Estonia | | | | | | |

An electrically insulating material, method for the preparation thereof, and insulated objects comprising said material

5 The present invention relates to an electrically insulating material comprising a thermoplastic polymer and a dielectric.

10 It is known to insulate high-voltage DC cables with paper impregnated with dielectric oil. The preparation of such insulated cables is cumbersome and time-consuming, as it comprises a number of steps, such as wrapping the paper round the electrical conductor, drying, impregnating the paper under heating, and cooling the insulation to ambient temperature. Such cables can also be used for alternating current.

15 By using the known insulations, local charge effects which may cause breakdown can be avoided, but the resulting cables are sensitive to quenching, and the operating temperatures should not exceed about 80 °C.

20 GB patent No. 1.371.991 discloses an insulation material, which is prepared by impregnating a porous, electrically insulating polymeric film with a dielectric fluid, followed by a heat-shrinkage of the polymeric film in view of encapsulating the dielectric fluid. The use of the known insulation material for insulating e.g. high-voltage cables is slow as, like the first-mentioned
25 insulating method, it presupposes that the impregnated polymeric film is wound round the electrical conductor.

30 It is also known to insulate high-voltage AC cables with an insulating insulation layer prepared by extrusion of a polymer, such as polyethylene or cross-linked polyethylene.

It has not been possible to use such insulation layers of a polymer for insulating high-voltage DC cables, i.a. because during cooling to ambient temperature at operating conditions, local charge effects are accumulated, thus entailing risk of breakdown.

Also, it is known to use various types of gels for insulation and/or field equalization.

US 4 943 685 discloses the use of a gel formed from a lightly cross-linked polymer and insulating fluid, such as a mineral oil, for injecting into e.g. cable splices or cable shoes, so that the gel fills out the void around the conductor and acts as insulation.

US 5 218 011 discloses the use of a gel composition comprising a fluid, a thickener, and a water absorbent polymer for incorporation as filler in cavities and in electrical cables. The main purpose of the presence of such a gel is to prevent entry of water, which i.a. is achieved in that the gel itself forms a barrier. If water does enter past this barrier, the water absorbent polymer is activated, and the water is absorbed. This type of gel is mainly used in connection with low direct voltages.

WO 86/01634 discloses use of a gelloid composition comprising a polymer, in which a fluid is dispersed, and optionally a filler, for field equalization in connection with electrical devices. The composition is especially well-suited for use at high voltages.

It is a common feature of these types of gels that they have no mechanical strength, for which reason they are most unfit for formation of a dimensionally stable insulation layer. Typically, it is the purpose of the gel to act as a mass which displaces air, as air is poorly insulating. As regards the gels mentioned in US 5 218 011

and WO 86/01634 there is the additional disadvantage that the particular gel in itself has no particular insulating effect, for which reason an additional insulation layer must typically be used.

5 JP 8302113A discloses the use of an ethylene-propylene rubber compounded with at least one compound selected from polybutene, polybutadiene, polysioprene, and butyl rubber, inorganic fillers, and organic peroxides for the preparation of an insulation material without use of
10 added oil.

Finally, WO 96/27885 discloses use of a composition comprising a polypropylene polymer or copolymer, polyethylene wax, and coated magnesium hydroxide as insulation or outer sheath for wires and cables. Such a
15 composition is easily extrudable, and the wax content ensures a smooth and wear-resistant surface.

Use of the above composition for high-voltage is, however, inexpedient because of the high content of magnesium hydroxide added in view of the fire retarding
20 effect of the substance.

It is the object of the present invention to provide a material which possesses sufficient insulating capacity for it to be used for both DC and AC insulation in connection with high-voltage, and which is easily
25 converted so as to form a desired insulation layer.

This object and other objects, which will be described in the following, are obtained with the insulation material according to the invention, which is characterized in that the thermoplastic polymer forms a continuous phase
30 incorporating an additional phase of a liquid or easily meltable dielectric in the form of a wholly or partly

interpenetrating network, and that the weight ratio of polymer to dielectric is between 95:5 and 25:75.

When using an electrically insulating material for e.g. high-voltage insulation, a temperature increase normally occurs, whereby the dielectric, if not already liquid, melts. Hereby a structure emerges comprising a solid network of polymer filled with liquid dielectric, which thereby gets to act as a mobile phase in the solid polymer network.

10 The presence of this mobile phase seems to prevent local charge effects, which in the known materials may cause breakdown, from arising, and without this phase inexpediently influencing the main structure and consequently the strength of the insulation material.

15 Examples of useful thermoplastic polymers include polyolefines, acetate polymers, cellulose polymers, polyesters, polyketones, polyacrylates, polyamides, and polyamines. The polymers may be homo-, co- or terpolymers. As co-monomers use can be made of various compounds with functional groups, such as epoxides, vinyls, amines, anhydrides, isocyanates, and nitriles. Mixtures of two or more polymers can also be used.

20 To avoid exudation of dielectric after the preparation of the insulation material, it is preferred to use low-crystalline polymers.

The liquid dielectric is preferably a mineral or synthetic oil, or a mixture of both. Low-viscosity as well as high-viscosity oils may be used.

30 Examples of use as dielectric oils include polyisobutylene, naphthenic, polyaromatic, and alpha-olefine containing oils, as well as silicone oils.

Examples of easily meltable dielectrics are wax and low molecular polymers.

In this context, the expression "easily meltable" should be taken to mean that the dielectric melts/softens at a lower temperature than the melting/softening temperature for the thermoplastic polymer.

The invention also relates to a method for the preparation of the electrically insulating material described above. This method is characterized in that the thermoplastic polymer and a liquid or easily meltable dielectric in a weight ratio from 95:5 to 25:75 of polymer to dielectric are mixed under heating to a sufficiently high temperature for melting both polymer and dielectric, that the mixture is optionally formed to a shape, and that it is cooled to ambient temperature. Hereby an insulation material is obtained which is dimensionally stable at temperatures of use, and consequently can be used without cross-linking as insulation material on e.g. high-voltage cables.

During the mixing and the heating of the thermoplastic polymer and the liquid or meltable dielectric, a liquid-in-liquid suspension is obtained, where the polymer as a result of its comparatively high viscosity predominantly forms a continuous phase, in which the liquid dielectric forms a similarly continuous, interpenetrating phase. It is presumed that a corresponding backbone structure is obtained after cooling the mixture to ambient temperature, however, with the difference that the polymer after having again assumed solid state forms a network containing a wholly or partly interpenetrating network of liquid of solidified dielectric.

It is understood that the said interpenetrating network is formed at microscopic level, and, as it is, is not

comparable with network at molecular level provided e.g. by cross-linking of polymer chains and/or formation of a gel structure.

- 5 The weight ratio of polymer to dielectric is, as mentioned, from 95:5 to 25:75. Particularly preferred ratios are from 90:10 to 50:50, and in particular from 90:10 to 75:25.

10 It may be advantageous to reinforce the polymer network in the insulating material according to the invention by evoking in the said mixture a cross-linking in the polymer. Such cross-linking can e.g. be obtained by radiation treatment or by admixing a cross-linking agent, e.g. in the form of a triallyl cyanurate, silanes or peroxides.

- 15 The mixture of polymer and dielectric can be added with one or more additives and/or fillers. For example, carbon black, titanium dioxide, wood powder or cellulose derivatives can be used for equalizing electrical fields.

20 The temperature to which the mixture is heated depends on the melting/softening point of the thermoplastic polymer, and should preferably lie more than 10 °C over this temperature. For α -olefines a temperature of up to 160 °C is typically used, and for e.g. polyamides, cellulose polymers, and polyketones a temperature up to 230 °C.

- 25 The thermoplastic polymer and the dielectric can be mixed and heated batch-wise or continuously, e.g. using an extruder. The mixed mass can be granulated and used as starting material for formation of desired insulation layers. For example, it can be extruded directly onto an
30 electrical conductor so as to form an insulation layer thereon, or by a multi-step extrusion of the electrically insulating material optionally added with carbon black or

another additive. The additive can also be added to the polymer prior to the mixing thereof with the dielectric.

Injection moulding, thermoforming or the like may also be used for the shaping.

- 5 The mixing and the heating as well as the extrusion onto a conductor may also take place in one step.

The invention further relates to objects, such as cables insulated with the electrically insulating material described above. Such insulated cables can be used for
10 both direct current and alternating current, preferably for direct current, and at voltages from 220 V to 10 MV. Preferred uses are for voltages greater than 5 kV, as the material at high field strengths is capable of maintaining its good electrical properties.

- 15 The insulation material described can also be used for other insulating purposes, e.g. for insulating terminations, cable splices, cable terminals, transformer insulation, for the preparation of dielectric components, for use in X-ray generators, and for other high-voltage
20 purposes.

In the following the invention is described in more detail with reference to the examples below.

Example 1

- 40 parts by volume of naphthenic oil with a viscosity at
25 25 °C of 12 cp were heated to 150 °C under stirring with a stirrer having a rotational speed of 30 rpm/min. Then 60 parts by volume of alpha-olefine containing polymer with an MFI of 0.6 g/10 min and a melting temperature of 142 °C were added. Mixing was for 4 min at 150 °C. The
30 mixture thus obtained was cooled and granulated at ambient temperature. The granulate was introduced into an

extruder and extruded in the form of a coating onto an electrical conductor at a temperature of 140-160 °C.

The insulating coating thus prepared was thermally stable and mechanically stable at temperatures up to about 80 °C. The coating consisting of two interpenetrating networks did not exude oil at a temperature of 80 °C and a superpressure of 1 bar.

By examining the breakdown strength of the insulating coating it was established that this strength was at least as high as for an insulating coating consisting of oil impregnated paper.

Example 2

An insulating coating was prepared on an electrical conductor by a method corresponding to that described in example 1, but using polyisobutylene oil instead of a naphthenic oil.

The coating obtained had essentially the same properties as the coating according to example 1.

Example 3

An insulating coating was prepared on an electrical conductor by a method corresponding to that described in example 1, with the exception that 70 parts by volume of polymer and 30 parts by volume of oil were used.

Example 3a

An insulating coating was prepared on an electrical conductor by a method corresponding to that described in example 1, however using 80 parts by volume of polymer and 20 parts by volume of oil.

The coatings obtained had essentially the same properties as the coating according to example 1.

Measurement of rate of local charging and discharging for the insulation materials prepared in examples 1, 3 and 3a was made by means of Pulsed Electro Acoustic Method (PEA). Test specimens were prepared from semi-conductor and have a thickness of 2 mm. Charging is effected with 20 kV DC voltage, and charging and discharging are for 24 hours. Measurements are made without impressed voltage on the test specimen.

Standard discharging rates for the materials from examples 1, 3 and 3a are stated in table 1 and compared with conventional AC PEX insulation and oil impregnated paper insulation.

| | PEX | Oil/paper | Polymer* | Ex. 1 | Ex. 3 | Ex. 3a |
|----------------------|-------|-----------|----------|-------|-------|--------|
| Unit | Min. | Min. | Min. | Min. | Min. | Min. |
| Decharg- ing time | > 500 | 200 | > 500 | 30 | 50 | 50 |

* alpha-olefinic polymer used in examples 1-3 and 3a

Table 1. Decharging rates for different dielectrics.

5 Example 4

An insulating coating was prepared on an electrical conductor by a method corresponding to that described in example 1, but using 10 parts by volume of paraffinic wax with melting interval of 57-60 °C from Merck, 80 parts of
 10 extrudable LDPE (from Dow), and 10 parts of powdered additive consisting of wood with a maximum diameter of 65 µm.

The insulation material obtained has essentially the same properties as the insulation in example 1.

15 Example 5

An insulating coating was prepared on an electrical conductor by a method corresponding to that described in example 1, but using 10 parts by volume of polycyclic oil with a density of 1.04/cm³, 89 parts of ethylene vinyl
 20 acetate (24% vinyl acetate) with an MFI of 3 g/10 min (2.16 kg/190 °C, ASTM D1238), and 1 part of powdered additive consisting of alumina trihydrate (Apyral 40 from Nabaltec) with a grain size diameter of about 1.5 µm.

The insulation material obtained has essentially the same
 25 properties as the insulation in example 1.

Example 6

An insulating coating was prepared on an electrical conductor by a method corresponding to that described in example 1, but using 5 parts by volume of chemically pure
5 oleic acid, 94.8 parts of ethylene acrylate with 2% maleic anhydride (Lotader 2100 from Elf Atochem), and 0.2 parts of powdered additive consisting of chemically pure titanium dioxide.

The insulating material obtained has essentially the same
10 properties as the insulation in example 1.

Example 7

15 parts by volume of epoxidized soybean oil were mixed with 85 parts of LDPE cable insulation polyethylene, into which 1.5 % of dicumyl peroxide had been premixed. The
15 mixing took place as described in example 1, however, mixing was at 135 °C. The insulation material thus prepared was cross-linked by heating to 180 °C under pressure (10 bar).

The coating material obtained has essentially the same
20 properties as the insulation in example 1.

C l a i m s :

1. An electrically insulating material comprising a thermoplastic polymer and a dielectric, c h a r a c -
t e r i z e d in that the thermoplastic polymer forms a
5 continuous phase incorporating an additional phase of a
liquid or easily meltable dielectric in the form of a
wholly or partly interpenetrating network, and that the
weight ratio of polymer to dielectric is between 95:5 and
25:75.
- 10 2. An electrically insulating material according to
claim 1, c h a r a c t e r i z e d in that the thermo-
plastic polymer is selected from a group consisting of
polyolefines, acetate polymers, cellulose polymers,
polyesters, polyketones, polyacrylates, polyamides,
15 polyamines, and epoxides, or a mixture of two or more of
these polymers.
3. An electrically insulating material according to
claim 1 or 2, c h a r a c t e r i z e d in that the
thermoplastic polymer is low-crystalline.
- 20 4. An electrically insulating material according to any
of the claims 1-3, c h a r a c t e r i z e d in that the
liquid dielectric is selected from a group consisting of
mineral or synthetic oils.
5. An electrically insulating material according to claim
25 4, c h a r a c t e r i z e d in that the dielectric oil
is selected from a group consisting of polyisobutylene
oils, naphthalenic oils, alpha-olefinic oils, and
silicone oils.
6. An electrically insulating material according to
30 claims 1-3, c h a r a c t e r i z e d in that the easily
meltable dielectric is a wax.

7. An electrically insulating material according to any of the preceding claims, characterized in that the weight ratio of polymer to dielectric is between 90:10 and 50:50, preferably between 90:10 and 75:25.
- 5 8. An electrically insulating material according to any of the preceding claims, characterized in that the material obtained is dimensionally stable.
9. A method for the preparation of an electrically insulating material from a thermoplastic polymer and a
10 dielectric, characterized in that a thermoplastic polymer and a liquid or easily meltable dielectric at a weight ratio between 95:5 and 25:75 of polymer to dielectric are mixed under heating to a
15 sufficiently high temperature for melting the thermoplastic polymer, that the mixture is optionally shaped, and that it is cooled to ambient temperature.
10. A method according to claim 9, characterized in that a cross-linking of the thermoplastic polymer is evoked in connection with the mixing and the
20 heating.
11. A method according to claim 10, characterized in that a cross-linking agent is introduced into the mixture of thermoplastic polymer and dielectric.
12. A method according to claims 9-11, characterized in that an additive, e.g. carbon black,
25 titanium dioxide, aluminium hydroxide, cellulose derivatives or wood powder, is added to the mixture of thermoplastic polymer and dielectric.
13. A method according to claims 9-12, characterized in that the thermoplastic polymer is added
30

with an additive or a filler prior to being mixed with the dielectric.

14. A method according to any of the claims 9-13, characterized in that the mixture is shaped
5 by extrusion.

15. A method according to claim 14, characterized in that the mixture is extruded as an insulation layer onto an electrical conductor.

16. An electrically insulated object comprising a
10 conductor and an insulation, characterized in that the insulation material is constituted by an insulating material according to any of the claims 1-8.

17. An electrically insulated object according to claim 16, characterized in that the insulation
15 surrounds an electrical conductor for voltages greater than 36 kV.

18. An electrically insulated object according to claim 16, characterized in that the insulation
20 surrounds an electrical conductor for voltages greater than 150 kV.

19. An electrically insulated object according to claim 16, characterized in that the insulation
surrounds an electrical conductor for voltages greater than 400 kV.

25 20. An electrically insulated object according to claims 16-19, characterized in that the conductor is intended for direct current.

21. Use of the electrically insulated material according to claims 1-8 for insulating cables.

22. Use of the electrically insulated material according to claims 1-8 for insulating cable assemblies, such as end terminations, fittings, cable splices, and cable terminals.
- 5 23. Use of the electrically insulated material according to claims 1-8 for the preparation of dielectric components for use in high-voltage equipment, such as X-ray generators.

AMENDED CLAIMS

[received by the International Bureau on 9 February 1999 (09.02.99);
original claims 1 and 23 replaced by new claims 1- 27 (4 pages)]

1. An electrically insulating material comprising a thermoplastic polymer and a dielectric having a weight ratio of polymer to dielectric between 95:5 and 25:75, wherein the thermoplastic polymer forms a network of solid polymer filled with a liquid or an easily meltable dielectric, said dielectric being able to act as a mobile phase in the solid polymer network.
2. An electrically insulating material according to claim 1, characterized in that the thermoplastic polymer forms a continuous phase incorporating the dielectric in the form of a wholly or partly interpenetrating network.
3. An electrically insulating material according to claims 1 or 2, characterized in that the thermoplastic polymer is selected from a group consisting of polyolefines, acetate polymers, cellulose polymers, polyesters, polyketones, polyacrylates, polyamides, polyamines, and epoxides, or a mixture of two or more of these polymers.
4. An electrically insulating material according to claim 1, 2 or 3, characterized in that the thermoplastic polymer is low-crystalline.
5. An electrically insulating material according to any of the claims 1-4, characterized in that the liquid dielectric is selected from a group consisting of mineral or synthetic oils.
6. An electrically insulating material according to claim 5, characterized in that the material comprises up to about 75 % by weight of oil.

7. An electrically insulating material according to claims 5 or 6, characterized in that the dielectric oil is selected from a group consisting of polyisobutylene oils, naphthalenic oils, alpha-olefinic oils, and silicone oils.
8. An electrically insulating material according to claims 1-4, characterized in that the easily meltable dielectric is a wax.
9. An electrically insulating material according to any of the preceding claims, characterized in that the weight ratio of polymer to dielectric is between 90:10 and 50:50, preferably between 90:10 and 75:25.
10. An electrically insulating material according to any of the preceding claims, characterized in that the material is dimensionally stable.
11. An electrically insulating material comprising a thermoplastic polymer and a dielectric having a weight ratio of polymer to dielectric between 95:5 and 25:75, wherein the thermoplastic polymer forms a network of solid polymer filled with a dielectric, said dielectric comprises a liquid or an easily meltable phase, which is able to act as a mobile phase in the solid polymer network.
12. A method for the preparation of an electrically insulating material from a thermoplastic polymer and a dielectric, characterized in that a thermoplastic polymer and a liquid or easily meltable dielectric at a weight ratio between 95:5 and 25:75 of polymer to dielectric are mixed under heating to a sufficiently high temperature for melting the thermoplastic polymer, that the mixture is optionally shaped, and that it is cooled to ambient temperature.

13. A method according to claim 12, c h a r a c t e r -
i z e d in that a cross-linking of the thermoplastic
polymer is evoked in connection with the mixing and the
heating.
- 5 14. A method according to claim 13, c h a r a c t e r -
i z e d in that a cross-linking agent is introduced into
the mixture of thermoplastic polymer and dielectric.
- 10 15. A method according to claims 12-14, c h a r a c -
t e r i z e d in that an additive, e.g. carbon black,
titanium dioxide, aluminium hydroxide, cellulose
derivatives or wood powder, is added to the mixture of
thermoplastic polymer and dielectric.
- 15 16. A method according to claims 12-15, c h a r a c -
t e r i z e d in that the thermoplastic polymer is added
with an additive or a filler prior to being mixed with
the dielectric.
17. A method according to any of the claims 12-16,
c h a r a c t e r i z e d in that the mixture is shaped
by extrusion.
- 20 18. A method according to claim 17, c h a r a c t e r -
i z e d in that the mixture is extruded as an insulation
layer onto an electrical conductor.
- 25 19. An electrically insulated object comprising a
conductor and an insulation, c h a r a c t e r i z e d
in that the insulation material is constituted by an
insulating material according to any of the claims 1-11.
20. An electrically insulated object according to claim
19, c h a r a c t e r i z e d in that the insulation
surrounds an electrical conductor for voltages greater
30 than 36 kV.

21. An electrically insulated object according to claim 19, characterized in that the insulation surrounds an electrical conductor for voltages greater than 150 kV.
- 5 22. An electrically insulated object according to claim 19, characterized in that the insulation surrounds an electrical conductor for voltages greater than 400 kV.
- 10 23. An electrically insulated object according to claims 19-22, characterized in that the conductor is intended for direct current.
24. Use of the electrically insulated material according to claims 1-11 for insulating cables.
- 15 25. Use of the electrically insulated material according to claims 1-11 for insulating cable assemblies, such as end terminations, fittings, cable splices, and cable terminals.
- 20 26. Use of the electrically insulated material according to claims 1-11 for the preparation of dielectric components for use in high-voltage equipment, such as X-ray generators.
27. An electrically insulating material obtainable by the method according to claims 12-18.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/DK 98/00382

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: H01B 3/44, H01B 3/20
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: H01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category* | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|-----------|--|-----------------------|
| A | EP 0749128 A2 (AT&T IPM CORP.), 18 December 1996 (18.12.96) -- | 1-23 |
| A | WO 9627885 A1 (SCAPA GROUP PLC), 12 Sept 1996 (12.09.96) -- | 1-23 |
| A | US 4060583 A (JAMES D. GROVES ET AL), 29 November 1977 (29.11.77) -- | 1-23 |

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

- * Special categories of cited documents:
- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "&" document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

4 January 1999

07-01-1999

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Jack Hedlund
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/DK 98/00382

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

| Category* | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|-----------|---|-----------------------|
| A | <p>File WPI, Derwent accession no. 79-51476B, FURUKAWA ELECTRIC CO LTD: "Insulation oil-filled plastic coated power cable mfr. - in which radiation heat resisting layer is formed to prevent plastic layer from being heated during sheathing"; & JP,A,54067689, 790531 DW7928</p> <p>-- -----</p> | 1-23 |

INTERNATIONAL SEARCH REPORT
Information on patent family members

01/12/98

International application No.
PCT/DK 98/00382

| Patent document cited in search report | | | Publication date | Patent family member(s) | Publication date |
|---|---------|----|---------------------|--|--|
| EP | 0749128 | A2 | 18/12/96 | NONE | |
| WO | 9627885 | A1 | 12/09/96 | AU 4885996 A CA 2214653 A CZ 9702816 A EP 0813741 A GB 9504705 D | 23/09/96 12/09/96 14/01/98 29/12/97 00/00/00 |
| US | 4060583 | A | 29/11/77 | AR 210755 A BR 7601276 A DE 2608477 A,B,C DK 65876 A SE 415132 B,C SE 7601835 A | 15/09/77 14/09/76 09/09/76 29/08/76 08/09/80 29/08/76 |